

CB FLOORPAINT

WATER-RESISTANT AND DIRT-REPELLENT DURABLE FLOOR COATING

PRODUCT DESCRIPTION

CB Floorpaint is a durable and water-repellent floor coating to protect concrete floors against repeated loading by cars and other vehicles. It prevents wear and tear caused by hot tyres and protects the surface against stains, grease and road salt. Thanks to its special composition, the **CB Floorpaint** is water-repellent and can be easily cleaned with everyday maintenance products. The colour is concrete grey (RAL 7023).

CHARACTERISTICS

- **Easy maintenance**
- **Resistant to stains and greases**
- **High resistance to repeated loading**
- **Contains no harmful solvents**

APPLICATIONS

Can be used for porous concrete floors indoors as well as outdoors. Can be applied on cement and concrete floors, for example in garages or basements, on stairs or window sills.

TECHNICAL DATA

Base	: Acrylate, co-polymer
Colour	: Concrete grey (RAL 7023)
Coverage	: 5m ² /L
Drying time	: Ca. 24h
Layers	: 2 (Primer coat and finishing coat)
Paintable	: Yes
Content	: 5L / 10L

PRECAUTIONS

Keep P102 out of the reach of children.

EUH 208 contains 1,2-benzisothiazol-3(2H)-one. May cause allergic reaction.

VOC limit value for this product (cat A/i): 140g/L (2010). This product contains 100 g/LP102

CONSUMPTION - STORAGE

Store in a cool (max. 20°C) and frost-free place. Do not process at ambient and substrate temperatures below +5°C and above 30°C. Use approx. 0.1 L/m² per layer. Stir before use.

Your tools can be cleaned with water immediately after work.

For a new concrete floor, wait 3 months before applying the coating.

Not suitable for combating rising and/or blowing moisture.

SURFACE PREPARATION

- First make the surface dust and grease free.
- Check whether the floor is sufficiently porous and absorbent.
Apply a few drops of water to the floor. If the drops penetrate the floor, it is sufficiently porous. If they bead on the floor surface, the floor is not porous enough and therefore not suitable for applying the floor

paint. Sand the floor with 80 grain sandpaper to remove shine from the surface or clean the floor with hydrochloric acid and water (1 litre of hydrochloric acid to 4 litres of water). Rinse the surface. Leave to dry for 48 hours. Repeat the 'drip test' and, if necessary, repeat the treatment (hydrochloric acid to 4 litres of water).

- Remove any loose cement, paint residues, salts and moulds with a steel brush.
- Seal cracks and tears with *CB 5 Snelcement*
- Rinse the prepared surface with water and allow to dry.

USER INSTRUCTIONS

- Apply **CB Floorpaint** with a brush or roller at a rate of approx. 0.1 L/m²/layer, use two layers.
- Dilute the first layer with 10% water to optimize adhesion.
- Apply a second layer undiluted after the first coat is completely dry. This takes about 24 hours.
- We recommend waiting 3 days before putting the treated area back into use.

CONSIDERATION - EPILOGUE

The information in this technical sheet is based on extensive research and experience. However, the information is provided without any guarantee - directly implied - as to its correctness. The conditions or methods of handling, storage, use of the product are beyond our control and may also be beyond our knowledge. For these and other reasons, we accept no liability for damage or nuisance of any kind, caused by the use of the product in question. The indicated characteristics and properties are average values and analyses obtained at 20 °C, deviations are tolerated. The rewrite of this sheet replaces all previous sheets.